



The
Enpro
Group

Product Name	% Total Solar Energy			% Visible Light			U Value	Emissivity	% UV Rejection	% Glare Reduction	Luminous Efficacy	Shading Coefficient	SHGC	% Infrared Rejection*	% Total Solar Energy Rejection
	Trans	Reflect (Ext)	Absorb	Trans	Reflect (Ext)	Reflect (Int)									
Designer Series															
Designer Grey 35	33.0	18.0	50.0	39.0	15.0	21.0	0.97	0.70	99.0	57.0	0.72	0.54	0.47	75.0	53.0
Designer Grey 45	43.0	13.0	44.0	49.0	12.0	13.0	1.01	0.78	99.0	45.0	0.77	0.61	0.56	65.0	44.0
Designer Grey 55	55.0	8.0	37.0	60.0	8.0	8.0	1.06	0.88	99.0	33.0	0.79	0.76	0.66	48.0	34.0
Softlite Series															
Softlite 25	15.0	39.0	46.0	23.0	28.0	33.0	0.92	0.61	99.0	75.0	0.72	0.32	0.28	92.0	72.0
Softlite 35	26.0	29.0	45.0	35.0	19.0	24.0	0.92	0.62	99.0	61.0	0.80	0.44	0.38	86.0	62.0
Starlite Series															
Starlite 8	6.0	53.0	41.0	8.0	56.0	25.0	1.03	0.82	99.0	92.0	0.37	0.21	0.18	97.0	82.0
Starlite 18	17.0	37.0	46.0	18.0	37.0	13.0	1.01	0.79	99.0	80.0	0.50	0.35	0.31	88.0	70.0
Starlite 28	22.0	33.0	45.0	29.0	31.0	20.0	1.02	0.79	99.0	68.0	0.72	0.40	0.35	87.0	65.0
Starlite 38	33.0	19.0	48.0	40.0	18.0	12.0	1.03	0.83	99.0	55.0	0.73	0.55	0.48	75.0	52.0
Advanced Ceramic Series															
Advanced Ceramic 3000	26.0	20.0	54.0	35.0	17.0	16.0	1.05	0.86	99.0	61.0	0.72	0.49	0.43	81.0	58.0
Advanced Ceramic 4000	36.0	16.0	49.0	46.0	14.0	12.0	1.06	0.88	99.0	49.0	0.79	0.59	0.51	71.0	49.0
Advanced Ceramic 5000	44.0	12.0	44.0	54.0	12.0	10.0	1.07	0.89	99.0	40.0	0.81	0.66	0.58	62.0	43.0
Advanced Ceramic 6000	51.0	10.0	38.0	63.0	10.0	9.0	1.09	0.93	99.0	29.0	0.87	0.72	0.62	52.0	38.0
Purelite Series															
Purelite 40	30.0	20.0	51.0	38.0	18.0	13.0	1.03	0.82	99.0	58.0	0.72	0.52	0.44	81.0	55.0
Purelite 60	43.0	9.0	48.0	60.0	10.0	11.0	1.04	0.85	99.0	33.0	0.91	0.66	0.57	85.0	43.0
Solar Safety Series															
Designer Grey 35 8Mil	30.0	18.0	52.0	36.0	15.0	22.0	0.98	0.73	99.0	60.0	0.69	0.52	0.45	79.0	55.0
Designer Grey 45 8Mil	37.0	16.0	47.0	44.0	14.0	17.0	0.97	0.71	99.0	51.0	0.76	0.58	0.50	73.0	50.0

© 2013 Madico, Inc. 5955041 9/13

Read in accordance with National Fenestration Rating Council (NFRC) standards on 3mm. (1/8") clear glass.

* IR Rejection is tested in the IR range of 780 to 2500 nanometers.